

TABLE 3 Legacy Drill Assay Highlights

Holeid	Zone	Feet			Metres			CuT	CuTSol	Mo
		From	To	Length	From	To	Length	%	%	%
ESC-010	enriched	954.7	974.4	19.7	291.0	297.0	6.0	0.59	0.55	0.007
	enriched	1,013.8	1,183.4	169.6	309.0	360.7	51.7	0.59	0.46	0.017
	including	1,013.8	1,034.0	20.2	309.0	315.2	6.2	0.85	0.81	0.039
	and	1,053.2	1,097.1	43.9	321.0	334.4	13.4	1.09	1.02	0.015
	primary	1,183.4	2,040.7	857.3	360.7	622.0	261.3	0.24	0.01	0.009
ESC-020	oxide	393.7	528.2	134.5	120.0	161.0	41.0	0.21	0.16	0.002
	including	413.4	452.8	39.4	126.0	138.0	12.0	0.37	0.34	0.003
	leached	570.2	592.5	22.3	173.8	180.6	6.8	0.10	0.04	0.001
ESC-024	oxide	144.4	177.2	32.8	44.0	54.0	10.0	2.13	2.00	0.003
	including	154.2	170.6	16.4	47.0	52.0	5.0	3.96	3.76	0.003
	enriched	196.9	219.8	23.0	60.0	67.0	7.0	0.11	0.10	0.002
	enriched	302.7	331.4	28.7	92.2	101.0	8.8	0.12	0.07	0.004
	enriched	434.7	498.7	64.0	132.5	152.0	19.5	0.31	0.30	0.002
	enriched	541.3	662.7	121.4	165.0	202.0	37.0	0.69	0.66	0.002
	including	584.0	633.2	49.2	178.0	193.0	15.0	1.03	1.02	0.001
	primary	662.7	754.6	91.9	202.0	230.0	28.0	0.23	0.02	0.004
ESC-028	oxide	308.0	337.9	29.9	93.9	103.0	9.1	0.48	0.47	0.003
	enriched	452.8	551.2	98.4	138.0	168.0	30.0	0.32	0.30	0.002
	including	528.2	551.2	23.0	161.0	168.0	7.0	0.53	0.51	0.002
	enriched	583.7	649.6	65.9	177.9	198.0	20.1	0.16	0.12	0.002
	primary	675.9	803.8	128.0	206.0	245.0	39.0	0.33	0.02	0.003
	including	754.6	797.2	42.7	230.0	243.0	13.0	0.44	0.02	0.004
ESC-030	leached	134.5	177.2	42.7	41.0	54.0	13.0	0.12	0.03	0.001
	oxide	252.0	306.4	54.5	76.8	93.4	16.6	0.14	0.06	0.001
	oxide	374.0	623.4	249.3	114.0	190.0	76.0	0.41	0.31	0.006
	including	390.4	436.4	45.9	119.0	133.0	14.0	0.73	0.53	0.002
	and	498.7	531.5	32.8	152.0	162.0	10.0	0.73	0.66	0.012
ESC-033	oxide	165.0	190.3	25.3	50.3	58.0	7.7	0.58	0.53	0.002
	enriched	275.6	364.2	88.6	84.0	111.0	27.0	0.57	0.53	0.003
	including	315.0	360.9	45.9	96.0	110.0	14.0	0.92	0.89	0.002
	enriched	646.3	721.8	75.5	197.0	220.0	23.0	0.30	0.27	0.002
	including	695.5	721.8	26.2	212.0	220.0	8.0	0.59	0.55	0.003
	enriched	843.2	990.8	147.6	257.0	302.0	45.0	0.15	0.10	0.001
	including	848.0	872.7	24.7	258.5	266.0	7.5	0.34	0.24	0.001
	primary	990.8	1,323.0	332.2	302.0	403.3	101.2	0.12	0.01	0.001
ESC-034	oxide	315.0	370.0	55.0	96.0	112.8	16.8	0.23	0.22	0.001
	enriched	370.0	465.0	95.0	112.8	141.7	28.9	0.24	0.22	0.001
	including	395.0	415.0	20.0	120.4	126.5	6.1	0.59	0.57	0.001
	oxide	540.0	660.0	120.0	164.6	201.2	36.6	0.23	0.20	0.001
	including	595.0	645.0	50.0	181.4	196.6	15.2	0.35	0.32	0.001
ESC-035	No significant intercepts									

ESC-036	oxide	240.0	285.0	45.0	73.1	86.9	13.7	0.10	0.06	0.001
ESC-037	oxide	255.9	272.3	16.4	78.0	83.0	5.0	0.15	0.13	0.001
	enriched	495.4	508.5	13.1	151.0	155.0	4.0	0.86	0.83	0.001
	oxide	572.1	629.9	57.8	174.4	192.0	17.6	0.66	0.54	0.001
	including	577.4	597.1	19.7	176.0	182.0	6.0	0.98	0.86	0.001
	enriched	629.9	682.4	52.5	192.0	208.0	16.0	0.41	0.39	0.002
	oxide	715.2	771.0	55.8	218.0	235.0	17.0	0.99	0.70	0.001
	including	748.0	769.0	21.0	228.0	234.4	6.4	1.29	0.88	0.001
	enriched	884.0	997.4	113.4	269.4	304.0	34.6	0.48	0.39	0.005
	including	896.4	921.9	25.6	273.2	281.0	7.8	1.07	0.92	0.003
ECC-038	oxide	728.0	780.8	52.9	221.9	238.0	16.1	0.80	0.72	0.005
	including	744.8	774.3	29.5	227.0	236.0	9.0	1.26	1.17	0.005
ESC-039	oxide	410.0	570.0	160.0	125.0	173.7	48.8	0.24	0.16	0.001
	including	425.0	455.0	30.0	129.5	138.7	9.1	0.44	0.33	0.001
ESC-040	leached	260.0	290.0	30.0	79.3	88.4	9.1	0.17	0.02	0.001
	oxide	560.0	590.0	30.0	170.7	179.8	9.1	0.31	0.23	0.001
ESC-041	enriched	790.0	810.0	20.0	240.8	246.9	6.1	1.40	1.38	0.001
	enriched	865.0	1,040.0	175.0	263.6	317.0	53.3	0.18	0.16	0.001
	including	915.0	950.0	35.0	278.9	289.6	10.7	0.27	0.25	0.001
	primary	1,040.0	1,060.0	20.0	317.0	323.1	6.1	0.13	0.04	0.001
ESC-042	enriched	1,056.4	1,080.5	24.1	322.0	329.3	7.3	0.23	0.11	0.001
ESC-043	Hole terminated in Gila Conglomerate above bedrock - mineralisation not tested									
ESC-044	oxide	295.0	335.0	40.0	89.9	102.1	12.2	0.16	0.05	0.001
	oxide	455.0	475.0	20.0	138.7	144.8	6.1	0.13	0.10	0.001
	enriched	510.0	625.0	115.0	155.5	190.5	35.0	0.27	0.27	0.001
	including	510.0	550.0	40.0	155.5	167.6	12.2	0.48	0.52	0.001
	primary	675.0	1,000.0	325.0	205.7	304.8	99.1	0.10	0.03	0.001
ESC-046	leached	255.0	275.0	20.0	77.7	83.8	6.1	0.12	0.02	0.001
	enriched	440.0	455.0	15.0	134.1	138.7	4.6	0.39	0.35	0.002
	enriched	515.0	690.0	175.0	157.0	210.3	53.3	0.68	0.65	0.004
	including	580.0	610.0	30.0	176.8	185.9	9.2	1.19	1.15	0.004
	and	645.0	690.0	45.0	196.6	210.3	13.7	1.01	0.98	0.003
ESC-047	enriched	643.0	682.4	39.4	196.0	208.0	12.0	0.46	0.45	0.008
	enriched	909.9	1,076.1	166.2	277.4	328.0	50.6	0.43	0.40	0.010
	including	1,049.9	1,076.1	26.2	320.0	328.0	8.0	0.92	0.85	0.018
	enriched	1,131.9	1,181.1	49.2	345.0	360.0	15.0	0.67	0.65	0.004
	enriched	1,230.3	1,446.9	216.5	375.0	441.0	66.0	0.60	0.51	0.011
	including	1,230.3	1,276.2	45.9	375.0	389.0	14.0	0.84	0.80	0.012
	and	1,401.2	1,433.7	32.5	427.1	437.0	9.9	1.67	1.27	0.014
	primary	1,446.9	1,554.1	107.3	441.0	473.7	32.7	0.18	0.03	0.007
ESC-049	oxide	315.0	345.0	30.0	96.0	105.2	9.2	0.15	0.12	0.002
	enriched	400.0	740.0	340.0	121.9	225.5	103.6	0.22	0.20	0.002
	including	400.0	455.0	55.0	121.9	138.7	16.8	0.56	0.54	0.001
	primary	740.0	900.0	160.0	225.5	274.3	48.8	0.12	0.02	0.001

ESC-050	enriched	584.7	623.6	38.8	178.2	190.1	11.8	0.10	0.09	0.002
	enriched	656.2	692.3	36.1	200.0	211.0	11.0	0.13	0.12	0.001
	enriched	803.8	899.0	95.1	245.0	274.0	29.0	0.15	0.12	0.002
	primary	899.0	1,306.5	407.5	274.0	398.2	124.2	0.14	0.02	0.001
ESC-051	RC Hole terminated 10ft into bedrock - mineralisation not tested									

TABLE 4 Legacy Drill Collars

HoleID	Easting (m)	Northing (m)	Elevation (ft)	TD (ft)	Azimuth	Dip	Type
ESC-010	421,428.6	3,644,468.1	1,359.0	2,180.0	0	-90	Core
ESC-020	422,588.0	3,643,635.4	1,379.9	932.0	0	-90	Core
ESC-024	422,000.7	3,644,053.9	1,382.9	1,016.5	0	-90	Core
ESC-028	422,071.8	3,644,125.5	1,385.0	1,213.0	230	-75	Core
ESC-030	422,175.8	3,643,881.0	1,379.9	919.5	230	-75	Core
ESC-033	421,820.3	3,644,228.9	1,384.4	1,493.0	235	-60	Core
ESC-034	421,693.1	3,644,023.2	1,377.5	660.0	230	-75	RC
ESC-035	421,503.1	3,643,977.5	1,374.8	530.0	230	-75	RC
ESC-036	421,870.0	3,643,974.3	1,379.2	595.0	230	-60	RC
ESC-037	421,712.7	3,644,024.4	1,377.7	1,246.0	230	-80	Core
ESC-038	421,635.4	3,643,786.3	1,373.1	1,023.0	230	-75	Core
ESC-039	421,984.7	3,643,751.7	1,375.5	830.0	230	-60	RC
ESC-040	421,816.9	3,643,604.9	1,370.7	960.0	230	-75	RC
ESC-041	421,975.3	3,644,692.1	1,398.1	1,060.0	230	-60	RC
ESC-042	422,473.6	3,644,457.9	1,397.8	1,183.0	225	-65	Core
ESC-043	422,619.6	3,644,575.0	1,402.6	417.0	230	-60	Core
ESC-044	422,152.6	3,644,504.0	1,394.1	1,000.0	230	-60	RC
ESC-046	421,847.4	3,644,566.4	1,393.3	690.0	230	-60	RC
ESC-047	421,740.1	3,644,684.8	1,395.5	1,557.0	230	-60	Core
ESC-049	421,989.1	3,644,380.9	1,390.4	900.0	230	-60	RC
ESC-050	421,913.0	3,644,478.6	1,392.4	1,306.5	230	-60	Core
ESC-051	421,759.1	3,644,502.4	1,390.8	380.0	230	-60	RC

1. Intervals are presented in core length and are drilled with inclinations between vertical to -60 degrees
2. Drill assays assume a mineralized cut-off grade of 0.1% CuT reflecting the potential for heap leaching of openpit material in the case of Oxide and Enriched or in the case of Primary material to provide typical average grades. Most holes were terminated prior to the basement fault.
3. Assay results are not capped. Intercepts are aggregated within geological confines of major mineral zones.
4. True widths are not known.